



U GROUP SRL
Via Borgomanero n° 1
28040 Paruzzaro (NO)

LEGAL DATA:
C.F e Reg.Imp.Novara: 02041920030
CCIAA Novara REA: 211799
P.IVA: IT02041920030
Codice Export: No015724
Cap.Soc.: 119.000 lv

CONTACTS:
WEBSITE: www.u-power.it/en
EMAIL: info@u-power.it
TEL: +39 0322 53 94 01
FAX: +39 0322 23 00 01

REV. 11/11/2024

DATA SHEET

PRODUCT PICTURE

RANGES

TECHNOLOGIES

SN20056 TROPHY S1PS FO SR
Natural Confort 11 Mondopoint
AirToe Aluminium
SHOE TYPE "A"
SIZE RANGE 35-48 (UK: 2-13)
Size tested: 42 - WEIGHT Kg 1,018



THE ROAR...



LEI&LEI



DESCRIPTION

TECHNICAL SPECIFICATIONS

EN ISO STANDARD

VALUE

Safety shoes low, light and comfortable U-Power of the The Roar range, with tumbled extra-strong breathable canvas with inserts in soft suede, aluminum toecap, anti-puncture, anti-slip and PU / PU LIGHT GRIP sole.

SAFETY TOE CAP "AirToe Aluminium"

Impact resistance. Free heights after collision mm
Compressive strength. Free heights after compr. mm

≥ 14
≥ 14

20345:2022

19,0
21,0

RESULT

INSOLE "Save & Flex PLUS® , pierce resistant "non metal"™"

Puncture resistance N

≥ 1100

Compliant

ELECTRICAL RESISTANCE CATEGORY

< 10⁹ Ω

N.A.

UPPER DYNAMIC WATERPROOFING AFTER 60'

Water absorption after 60'
Water transmitted after 60'
Permeability to water vapor mg/(cm² h)
Permeability coefficient mg/cm²

≤ 30%
≤ 0,2 gr
≥ 0,8
≥ 15

N.A.
N.A.
17,5
142

VAMP LINING

Permeability to water vapor mg/(cm² h)
Permeability coefficient mg/cm²
Resistance to abrasion - DRY cycles
Resistance to abrasion - WET cycles

≥ 2
≥ 20
25.600 cycles
12.800 cycles

19,0
153
Compliant
Compliant

INSOLE

Abrasion resistance

≥ 400 cycles

No damage

SOLE WEAR

Abrasion resistance (volume loss) mm³
Bending resistance mm
Resistance to sole / midsole detachment N/mm
Hydrocarbons resistance (% volume variation)
Heel energy absorption J

≤ 150
≤ 4
≥ 3
≤ 12
≥ 20

38
0,4
4,1
3,2
30

SLIP RESISTANCE

Slip resistance on ceramic with NaLS (forward heel 7°)
Slip resistance on ceramic with NaLS (backward forepart 7°)
SR-Slip resistance on ceramic with glycerin (forward heel 7°)
SR-Slip resistance on ceramic with glycerin (backward forepart 7°)

≥ 0,31
≥ 0,36
≥ 0,19
≥ 0,22

0,42
0,47
0,23
0,30